

AWG (AMERICAN WIRE GAUGE) ÇEVİRİM TABLOSU / AWG (AMERICAN WIRE GAUGE) CONVERSION TABLE

İletken Conductor						
AWG No.	n x AWG	mm	mm ²	Ø mm	Ω/km	Kg/km
36	Solid	Solid	0,013	0,127	1460,0	0,116
36	7/44	7x0,05	0,014	0,152	1271,0	0,125
34	Solid	Solid	0,020	0,160	918,0	0,178
34	7/42	7x0,064	0,022	0,192	777,0	0,196
32	Solid	Solid	0,032	0,203	571,0	0,284
32	7/40	7x0,078	0,034	0,203	538,0	0,302
32	19/44	19x0,05	0,037	0,229	448,0	0,329
30	Solid	Solid	0,051	0,254	365,0	0,450
30	7/38	7x0,102	0,057	0,305	339,0	0,507
30	19/42	19x0,064	0,061	0,305	286,7	0,543
28	Solid	Solid	0,080	0,330	232,0	0,710
28	7/36	7x0,127	0,087	0,381	213,0	0,774
28	19/40	19x0,078	0,091	0,406	186,0	0,810
27	7/35	7x0,142	0,111	0,457	179,0	0,988
26	Solid	Solid	0,128	0,409	143,0	1,14
26	10/36	10x0,127	0,127	0,533	137,0	1,13
26	19/38	19x0,102	0,155	0,508	113,0	1,38
26	7/34	7x0,160	0,141	0,483	122,0	1,25
24	Solid	Solid	0,205	0,511	89,4	1,82
24	7/32	7x0,203	0,227	0,610	76,4	2,02
24	10/34	10x0,160	0,201	0,582	85,6	1,79
24	19/36	19x0,127	0,241	0,610	69,2	2,14
22	Solid	Solid	0,324	0,643	55,3	2,88
22	7/30	7x0,254	0,355	0,762	48,4	3,16
22	19/34	19x0,160	0,382	0,787	45,1	3,4
22	26/36	26x0,127	0,330	0,762	52,3	2,94
20	Solid	Solid	0,519	0,813	34,6	4,61
20	7/28	7x0,320	0,562	0,965	33,8	5,0
20	10/30	10x0,254	0,507	0,889	33,9	4,51
20	19/32	19x0,203	0,615	0,940	28,3	5,47
20	26/34	26x0,160	0,523	0,914	33,0	4,65
18	Solid	Solid	0,823	1,020	21,8	7,32
18	7/26	7x0,404	0,897	1,219	19,2	7,98
18	16/30	16x0,254	0,811	1,194	21,3	7,22
18	19/30	19x0,254	0,963	1,245	17,9	8,57
18	41/34	41x0,160	0,824	1,194	20,9	7,33
18	65/36	65x0,127	0,823	1,194	21,0	7,32

